



Made in Germany!  
Importer: Ltd "Abschliff Latvija"  
Riga, A Čaka iela 107 K2  
Phone: +371 67843844, 67843845  
Fakss: +371 67272792  
Mob.: +371 26177888  
E-mail: [info@abschliff.lv](mailto:info@abschliff.lv)  
[www.abschliff.lv](http://www.abschliff.lv)

[ps://www.facebook.com/Abschliff-Latvija-100679528475676/](https://www.facebook.com/Abschliff-Latvija-100679528475676/)

Open: Monday to Friday – 9<sup>00</sup>-18<sup>00</sup>, Saturday- 10<sup>00</sup>-14<sup>00</sup>, Sunday – closed



## Avalon Wetterschutzfarbe - protection of all timberwork outdoors

### Description

Excellent hiding power, produces an elastic film, water vapour permeable, contains film protection against fungi. Not suitable for window rebates, seatings and flooring. Not suitable for horizontal surfaces in exposed outdoor areas! Saliva and perspiration fast according to DIN 53160.

### Application range

Open-pored finishing coat for all exterior wood. Especially suitable for roughly-cut wood.

### Colour

014 Corn yellow, 057 Swedish red, 064 Earthen brown, 104 Vine black, 123 Frisian blue, 204 Old white, 400 Fir green, 401 Steel grey, 733 Anthracite grey.

### Ingredients

Linseed oil-wood oil- natural resin-ester, wood oil-ricinen oil-stand oil, linseed oil-wood oil-stand oil, wood-oil-stand oil, linseed oil, natural resin-ester, isoparaffins, kaolin, chalk, silicic acid, alumina, microwax, mineral pigments, zinc carbonate, jodo-propynyl-butyl-carbamate, drying agents. The product contains max 290 g/l VOC. EU limit value for this product (cat. e): 400 g/l (2010)

### Application

Stir well before use. Apply by brush, roller or spraying at temperatures above 15°C. The product is ready for use. Always apply a test coat. Ensure good light and ventilation conditions during use and drying times.

### Drying time

At 20°C and 50 - 55% relative humidity dust dry after approx. 12 hours. Dry and reworkable after approx. 24 hours. The product needs sufficient air for drying. Ensure good light and ventilation conditions during use and drying times. In case of low air exchange use a ventilator to avoid odors

### Packaging and consumption

Approx. 55 - 85 ml/m<sup>2</sup> per coat on planed respectively sanded wood. In case of roughly-cut wood the consumption will be slightly higher. Apply sparingly to avoid disturbances of the drying process!

Packaging: 0.75l for 10,5 m<sup>2</sup>, 2.5l for 35 m<sup>2</sup>

### Storage

Under cool and dry conditions. Close lid tightly when not in use. Shelf-life of unopened container 5 years.

### Disposal

According to locally regulated laws. European Waste Catalogue (EWC) 08 01 11.

### Cleaning up

Clean surfaces with neutral detergents in lukewarm water. Clean equipments immediately after use with solvents.

### Precautionary statements

Keep out of reach of children. IF SWALLOWED: Call a POISON CENTER/doctor if you feel unwell. Do NOT induce vomiting.

Weatherproof Paint 850 Avoid release to the environment. Dispose of contents/container according to local regulations. Always be sure to store cleaning cloth, polishing pads, sponges, etc. that are still wet or even slightly moist with product in an airtight metal container or in water and dispose, as there is a danger of spontaneous combustion caused by the plant oil content in the product. The product alone will not undergo spontaneous combustion. A typical smell may arise due to the natural raw materials. During sanding wear mask against respirable dust.

Safety data sheet available on request.

### Hazard statements

Repeated exposure may cause skin dryness or cracking. Contains Iodo-2-propynyl-butylcarbamate. May produce an allergic reaction. Active ingredient: Iodo-2-propynyl-butylcarbamate <0,6% Safety data sheet available on request. Warning! Hazardous respirable droplets may be formed when sprayed. Do not breathe spray or mist.

To achieve optimum results, please refer to the Technical Data Sheets of all products used. The information is based on our current knowledge and experience. However, they do not constitute a guarantee of product properties and do not establish a contractual legal relationship. With the publication of this Technical Data Sheet, all previous information becomes invalid. Status: March 28, 2023

