



**Made in Germany!**  
Importer: Ltd "Abschliff Latvija"  
Rīga, A Čaka iela 107 K2  
Phone: +371 67843844, 67843845  
Mob.: +371 26177888  
E-mail: [info@abschliff.lv](mailto:info@abschliff.lv)  
[abschliff.lv](http://abschliff.lv)



**Open: Monday to Friday – 9<sup>00</sup>-18<sup>00</sup>, Saturday- 10<sup>00</sup>-14<sup>00</sup>, Sunday – closed**

## BergerBond P2S – 2-component adhesive

**Description:** BergerBond P2S is a 2-component adhesive on the basis of high-quality polyurethane raw materials and is recommended for fixed adhesion of mosaic flooring, upright multilayer parquet, lamparquet, strip parquet, solid wood floors, ( $t < 22$  mm  $l < 2200$  mm), solid wooden boards (bigger formats), solid wood (10mm) parquet, and most exotic woods. The product can also generally be used for adhering twolayer parquet, three-layer parquet, and wood block paving (RE), however, the use of BergerBond M1P is preferable with these. BergerBond P2S is also best suited for the gluing of water-sensitive types of wood such as beech, maple and ash because of the property "free of bulging and deforming." BergerBond P2S is solvent-free, contains no water and is suitable for chair casters. The product performs a very long open time. Giscode: RU1. Emicode: EC1. AbZ-Nr. Z-155.20-49. ATFA: Compliant. NWFA: Compliant. MFMA: Compliant. Breeam: Compliant.



BERGERBOND

**Technical data:** Mixing ratio: 8:1 by weight. Processing/laying time: 50-60 min. Fit for walking on after: 4-6 h. Fit for further work after: 12 h. Final hardness after: 48 h. Flash-off time: no. Suitable for in-floor heating: yes. All data are based on standard climate (23°C and 50% rel. humidity). If the conditions differ from this standard, the times will differ too!

**Special tips:** Do not use BergerBond P2S in conditions below + 15°C or above 65% rel. humidity. In the cold season adhesive and flooring elements should be given time to reach the same temperature..

**Application:** Homogeneously mix components A and B and stir at least 3 min. with an appropriate mixer. The mixing is finished when the adhesive has reached a uniform color. After that BergerBond P2S can be evenly applied with an appropriate serrated trowel (BergerTool Zahnpachtel B3, B7, B11, B15). Don't cover with adhesive more than 1 m<sup>2</sup> at one time. Immediately lay the flooring elements, thoroughly press. Be sure that the flooring elements' underside is completely covered with adhesive. Follow the structural components extension joints.

**Consumption:** 800-1.300 g/m<sup>2</sup> (50-70 sf/gal) depending on trowel serration, flooring type and subfloor.

**Subfloor:** The subfloor must be clean (free of contaminations), dry (permanently dry!), firm, plane and free of cracks. The requirements of DIN 18356 "Wood flooring works" or of DIN 18367 "Wood paving works", as appropriate, must be met. BergerBond P2S can be combined with BergerBond Primer P and BergerBond Primer E or BergerBond Primer D (for example to dust binding in a mixing ratio of at least 1:3 with water). If there is a risk of rising moisture, one has to check whether the relevant rules referring to the sealing against moisture have been complied with. In case of underfloor heating and of absorbing subfloors, such as anhydrite or magnesite screeds, priming needs to be checked. The primer coat must dry sufficiently.

**Storage / transport:** Can be stored for at least 12 months (adhesive and hardener) if transported and stored in cool and dry conditions, and if the original packaging is not opened. Protect from frost!

**General remark:** Please read the instructions carefully before processing this product. This Berger-Seidle product must be processed by a qualified person for parquet laying, for whom this manual is intended. The activities shall be carried out in accordance with the rules of the craft, the state of the art and the applicable standards and regulations of the country in which the product is used. The specifications of DIN 18356 "Parquet and wood paving" and DIN 18365 "Flooring work", information sheets and technical information of the TKB, the BEB, the CTA and the BVPF-Bundesverband Parkett & Fußbodentechnik must be observed. The customer must be informed about the cleaning and care specifications of the product. Any use that does not conform to the scope of Berger-Seidle's application is considered improper. The improper use and non-compliance with the instructions in this manual is largely the responsibility of the processor and as a result excludes the manufacturer's liability and warranty. Before using the product, the general conditions for use must be checked properly and professionally.

**Cross reference:** The following Technical Data Sheets should be observed:

- General recommendations for the usage of parquet and flooring adhesives
- Marking and safety recommendations (MSDS)
- Installation instructions by hardwood flooring manufacturers and valid standards

\* If the content of the Technical Data Sheet differs from other printed material, e.g. labels, the current version of the Technical Data Sheet on the homepage is always deemed valid. Printed material is always adapted when reprints are made.